

Property of No.6360 (for BGA ,CSP)

Item No.		No.6360-15	No.6360-25	No.6360-55 (Trial)	No.6360-75 (Trial)
Thickness (μm)	Backing	150	150	150	150
	Adhesive	10	10	10	20
Adhesion (N/10mm) () :After UV	SUS	2.9 (0.22)	4.1 (0.22)	2.8 (0.13)	6.7 (0.51)
	Glass	3.4 (0.23)	4.4 (0.23)	2.6 (0.14)	7.0 (1.20)
	Si (mirror)	3.4 (0.28)	4.6 (0.26)	2.4 (0.10)	6.8 (0.96)
	GE	3.0 (0.43)	4.0 (0.16)	—	5.5 (0.60)
Holding Power	40°C/24h	< 0.1mm	< 0.1mm	< 0.1mm	800min
Tensile Strength (TD/MD) (N/10mm)	Before UV	30/30	30/30	32/29	32/31
	After UV	24/24	24/24	25/26	26/24
Elongation (TD/MD) (%/10mm)	Before UV	900/840	910/840	900/880	830/880
	After UV	810/750	810/750	810/780	750/770
Remark		Smooth Surface	Smooth Surface	Smooth Surface	Rough Surface